



Technical Data Sheet

Nov. 03, 2020

C-POXY 30

Description: *C-POXY 30* is a general purpose structural-unfilled-fast setting epoxy adhesive. Recommended for bonding metal, ceramics, stone, glass, concrete, wood, fiberglass and many plastics such as polyester, ABS and rigid PVC (not suitable for PTFE-PP-PE and rubbers).

Physical properties:

	<i>PART A (Resin)</i>	<i>PART B (Hardener)</i>
Composition	Epoxy resin	Polymercaptan
Viscosity (25°C -cps)	11000-13000	12000-14000
Color	Colorless/Clear	Colorless/clear
Specific Gravity @ 25°C	1.19	1.12
Mixing ratio (volume)	1	1

Curing behavior:

At 25°C:

Pot life (time detected using 6g total mass)	20-40 minutes
Cure Time (functional)	60-90 minutes
Mixing color	Colorless-clear
Shear strength (ISO4587)	11-15 N/mm²
Hardness (Shore D)	75-80
Gap to fill	0.1-2.1 mm

Chemical Resistance (after 24 hours from curing):

Chemical	Temperature	After 100 hours	After 500 hours
Motor oil	40°C	EX	EX
Water	25°C	EX	EX
Cooling Gas	25°C	EX	EX
Gasoline	25°C	EX	EX

Directions for use:

Part A and B need to be mixed thoroughly in the correct volume ratio for minimum 1 minute before use. Gel time of the mixed product is 20-40 minutes at room temperature.

Parts requiring bonding should be assembled and kept close without any stress. Assembling is continued until full curing takes place.

Excess of the product can be cleaned with Acetone or any solvent-based cleaner compatible with the substrates to bond.

For best results, it is recommended to scratch (if possible) the surface, then gently degrease and clean the excess material off the area.

Note: Shear strength will increase roughly to 25-27 N/mm² if bonding parts are allowed to cure 50 minutes at room temperature 25°C(77°F) followed by 2 hours cure at 100°C(212°F) (if possible).

Storage: Product must be kept in a cool and dry room at 10°C to 25°C.

Shelf life: Minimum two (2) years in unopened packaging at +5°C / +27°C.

Safety and handling: Consult Material Safety Data Sheet (MSDS) before use.

Note: The data contained herein is obtained in CECCORP Laboratories and is provided for the sole purpose of informing. We do not accept responsibility for the results obtained by others whose methods are not under our control. It is the user's responsibility to determine suitability for their purpose of any product mentioned herein. CECCORP disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose. CECCORP specifically disclaims any liability for consequential or incidental damages of any kind, including loss of profit.